

H&I Chemicals Ltd

Hesketh House, 5 Ashfield Road
Chorley, Lancashire, PR7 1LH

Tel: 01257 261633

Email: Sales@hichemicals.com



SALES SPECIFICATION

COPPER OXYCHLORIDE 50% WP

Description:	Copper oxychloride water dispersible powder
Appearance:	Bluish green free flowing powder
Total Copper content:	50 % m/m min.
Copper soluble in water:	5000 ppm max.
Arsenic:	50 ppm max.
Lead:	250 ppm max.
Cadmium:	50 ppm max.
pH of aqueous dispersion:	6.0 – 9.5
Wet sieve test (on 45micron test sieve):	1.0 % m/m max.
Suspensibility:	80 % m/m min.
Persistent foam:	10 ml max.
Wetting of product:	60 sec. max.
Storage stability at 54°C for 14days	Complies with wet sieve test and suspensibility

Issue Date; June 2025.