

H&I Chemicals Ltd

Hesketh House, 5 Ashfield Road
Chorley, Lancashire, PR7 1LH

Tel: 01257 261633

Email: Sales@hichemicals.com



SALES SPECIFICATION

LAROFLEX MP35

Appearance:	Fine White Powder
Viscosity (20% Solution in Toluene):	30 – 40 mPa-s
Shear Rate D:	500 s ⁻¹
K Value:	35
Density at 20°C:	1.24 g/cm ³
Vicat Softening Temp:	48 – 52°C
Chlorine Mass Fraction:	44%

Issue Date: January 2024