

H&I Chemicals Ltd

Hesketh House, 5 Ashfield Road
Chorley, Lancashire, PR7 1LH

Tel: 01257 261633

Email: Sales@hichemicals.com



SALES SPECIFICATION

PVB RESIN B-08HX

Butyral content:	76 – 82 % wt / wt
Hydroxyl content:	18 – 21 % wt / wt
Acetate content:	< 3.0 % wt / wt
Viscosity:	110-180 cps (10% sol. in toluene / ethanol 1:1 at 20°C by Brookfield viscometer)
Free Acid:	< 0.05% wt / wt
Volatile:	< 3.0 % wt / wt

PROPERTIES:

Appearance:	White Powder
SG	1.1 g/cm ³
Bulk Gravity	0.25 – 0.35 g/cm ³
Glass transition temp:	68°C approx.

Issue Date: January 2024