

H&I Chemicals Ltd

Hesketh House, 5 Ashfield Road
Chorley, Lancashire, PR7 1LH

Tel: 01257 261633

Email: Sales@hichemicals.com



SALES SPECIFICATION

URETHANE ALKYD RESIN SMK 5462-WS

SMK-5462 is a Urethane modified long oil alkyd resin composed of linseed oil.

Composition

Oil Type:	Linseed Oil
Oil Length:	~62 %
Solvent:	White Spirit
Appearance:	Clear

Test	Range	Method
Non-Volatile:	50±2 %	ISO 3251
Viscosity (25°C) Pa.s (70%):	1 – 3	ISO 3219
Acid Value (mg KOH/g):	4 Max	ISO 2114
Colour (Gardner):	8 Max	ISO 4630-2
Density (gcm ³):	0.93 ± 0.02	ISO 2811-1

Solvent Solubility

Toluene:	✓
Xylene:	✓
White Spirit:	✓
n-Butanol:	X
Methyl Ethyl Ketones:	✓
Glycol Ethers:	✓

H&I Chemicals Ltd

Hesketh House, 5 Ashfield Road
Chorley, Lancashire, PR7 1LH

Tel: 01257 261633

Email: Sales@hichemicals.com



Resin Type Compatibility

Rosin Esters:	X
Amino Resins:	X
Short Oil Alkyds:	X
Medium Oil Alkyds:	✓
Long Oil Alkyds:	✓
Aliphatic Hardeners:	✓
Aromatic Hardeners:	✓
Cellulosic Resin:	X
Phenolic Resin:	X

Recommended Drier Combinations:

Cobalt:	0.04 – 0.06 %
Zirconium:	0.05 – 0.07 %
Calcium:	0.08 – 0.10 %

(As metals in relation to 100% resin)